

Unic Film W-Series white EV21119

Unic Film W-Series white (EV21119) displays a very well-balanced property profile, such as a high abrasion and wear resistance, a low sliding friction coefficient as well as a high impact strength; non-conductive; test certificate and test report pursuant to EU Regulation No 10/2011 are available; FDA compliant, for which reason present series is particularly applied and used in the food and beverage industry, in the storage and packaging industry as well as in the mechanical engineering sector.

	Test Method	Unit	Value
General Physical Properties			
density	DIN EN ISO 1183	g/cm ³	0.94
molecular weight (1)		10 ⁶ g/mol	5
Thermal Properties (2)			
melting temperature (DSC, 10 K/min)	DIN 3146	°C	135
heat conductivity (+23 °C)	DIN 52612-1	W/(m*K)	0.41
average coefficient of linear thermal expansion (23 to 60 °C)	ISO 11359 parts 1 and 2	°C ⁻¹	~ 2*10 ⁻⁴
service temperature, long term (3)	reference values	°C	-200 ... 80
service temperature, short term (max) (4)	reference values	°C	130
Mechanical Properties			
ultimate elongation at break (5)	DIN EN ISO 527-1/-2	%	500
tensile modulus of elasticity (5)(6)	DIN EN ISO 527-1/-2	MPa	500
notch impact strength (7)(2)	DIN EN ISO 11542 part 2	kJ/m ²	≥ 210
shore hardness (8)	DIN EN ISO 868	D scale	65
Electrical Properties			
contact resistance	DIN EN 60079-0 and/or 13463-1	Ω * cm	>10 ¹⁴
surface resistance	DIN EN 60079-0 and/or 13463-1	Ω	>10 ¹³
dielectric strength (9)	DIN EN 60079-0 and/or 13463-1	kV/mm	≥ 45

The values indicated herein are mean values safeguarded by continuous monitoring and recurring testing. Present data exclusively represent the properties of the materials (indicative values) – unless expressly agreed, they shall not be contractually guaranteed.

- (1) This is the average molar mass of the PE-UHMW (= ultra-high molecular weight polyethylene) resins – irrespective of any additives – used for the manufacture of this material. It is calculated by means of the Margolis equation $M = 5.37 \times 10^4 \times [\eta]^{1.49}$ with $[\eta]$ being the intrinsic viscosity (Staudinger index), derived from a viscosity measurement according to ISO 1628-3:2001, using decahydronaphthalene as a solvent (concentration of 0.0002 g/cm³).
- (2) The values given for these properties are, for the most part, derived from raw material supplier data (material data sheet) as well as from other publications.
- (3) Valid only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- (4) Temperature resistance over a period of 20,000 hours. After this period of time, there is a decrease in tensile strength – measured at 23 °C – of approximately 50% as compared with the original value. The maximum allowable service temperature indicated herein is thus based on the thermal-oxidative degradation taking place, causing a reduction in properties. Note, however, that in many cases the highest admissible service temperature essentially depends on the duration and the magnitude of the mechanical load/stress the material is subjected to during heat exposure.
- (5) Average values from test specimen taken (machine direction orientation)
- (6) Test speed: 1 mm/min
- (7) With 14° sharp, double-sided V-notch
- (8) Measured on 10 mm thick test specimens for a duration of 15 seconds
- (9) Electrode configuration: two (2) coaxial cylinders (ø25 mm / ø75mm); in transformer oils according to IEC (= International Electrotechnical Commission) Regulation No 60296; measured on 1 mm thick test specimen. It is important to note that the dielectric strength of UniC Film black may be considerably lower than the value indicated in the table for UniC Film off-white.

Present table shall provide valuable assistance in the choice of material. The data listed herein are within the normal range of product properties. However, they are not guaranteed and they should neither be used to establish material specifications/specification limits nor should they be consulted as a basis of design.

All data, information and/or recommendations supplied/provided by or on behalf of cps GmbH in relation to its products, in any form, is/are supported by research and may thus be considered to be reliable. Nevertheless, cps GmbH shall not assume any liability whatsoever in respect of application, processing, and/or any other utilization of the aforementioned information and/or products, or any consequence thereof. The buyer shall undertake all liability in respect of the application, processing and/or utilization of the aforementioned information and/or products, the quality and other properties of which he shall verify, or any consequence thereof. No liability whatsoever shall attach to cps GmbH for any infringement/violation of the rights owned or controlled by a third party in intellectual, industrial and/or other property by reason of the application, processing and/or utilization of the aforementioned information and/or products by the buyer.